

• TRUSTED QUALITY SINCE 1921 •

**RUST-OLEUM®**  
SPECIALTY**SPECIALTY  
TUB & TILE TOUCH-UP PAINT****DESCRIPTION AND USES**

Rust-Oleum® Specialty Tub & Tile Touch-Up Paint repairs chips, scratches, dents and defects on porcelain, ceramic, fiberglass, acrylic cast iron and steel surfaces that are subject to water exposure. It is a washable, moisture resistant finish that is suitable for use on tubs, tiles, sinks and toilets. This durable two-component epoxy acrylic provides a high gloss finish to make such surfaces look newer.

Do not use on surfaces exposed to temperatures over 200°F (93°C) such as stove tops, areas of constant high humidity and water immersion such as swimming pools, hot tubs, saunas, or for use on galvanized steel or flexible plastic.

**PRODUCTS****SKU (0.45 ounces)      Description**

244166	White
--------	-------

**PRODUCT APPLICATION****PAINTING CONDITIONS**

Use when air and surface temperature is between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C).

**SURFACE PREPARATION**

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with soap and water. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces.

**PRODUCT APPLICATION (CONT.)****SURFACE PREPARATION (cont.)**

**WARNING!** If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you sand, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**APPLICATION**

Mix each bottle by rolling between palms for 5 minutes. Pour all contents of part A into part B. Mix part B bottle again by rolling between palms for 5 minutes. Note: Use the product within 24 hours of mixing the two components. Apply Tub & Tile Touch-Up using even strokes. For deep scratches or chips, apply multiple layers allowing 10 minutes between coats. For best results, allow to dry for 3 days before exposing the surface to water. More than 2 coats will require additional cure time. **Do not use near open flame.**

**DRY and RECOAT TIMES**

Based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 20 minutes, to handle in 1 hour and is fully cured in 3 days.

**CLEAN-UP**

Clean up any excess product with lacquer thinner, rubbing alcohol or acetone.

## TECHNICAL DATA

# SPECIALTY TUB & TILE TOUCH-UP PAINT

## PHYSICAL PROPERTIES

		TUB & TILE TOUCH-UP PAINT
Resin Type		Epoxy Modified Acrylic
Pigment Type		Titanium Dioxide
Solvents		Ethylbenzene, Propylene Glycol Monomethyl Ether, Xylene
Weight	Per Gallon	10.5 lbs.
	Per Liter	1.3 kg
Solids	By Weight	61.2%
	By Volume	50.9%
Volatile Organic Compounds		<500 g/l (4.16 lbs./gal.)
Recommended Dry Film Thickness (DFT) per Coat		2.0-3.0 mils (50-75μ)
Wet Film to Achieve DFT (unthinned material)		4.0-6.0 mils (100-150μ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		0.75-1.25 sq.ft./bottle (0.45 ounces)
Dry Times at 70-80°F (21°-27°C) and 50% Relative Humidity	Touch	20 minutes
	Handle	1 hour
	Recoat	Allow 10 minutes between coats
Dry Heat Resistance		200°F (93°C)
Shelf Life		3 years
Flash Point		51°F (11°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.