



# STOPS RUST® TEXTURED SPRAYS

## DESCRIPTION AND USES

Rust-Oleum® Stops Rust® Textured Sprays are designed to provide a durable protective coating with excellent resistance to rust, and excellent resistance to abrasion, fading, chipping, and dulling. These sprays apply easily, provide excellent coverage and dry fast to a tough attractive finish. Rust-Oleum Stops Rust Textured Sprays are ideal for outdoor metal surfaces. These sprays feature a comfort tip with a wider finger pad to reduce fatigue caused by continuous spraying. Not for use on galvanized metal.

## PRODUCTS

### SKU DESCRIPTION (Aerosol)

#### MULTICOLOR TEXTURE

223523	Autumn Brown
223524	Desert Bisque
223525	Aged Iron
223526	Deep Forest
239119	Sea Green
239120	Radiant Brass
239121	Caribbean Sand
239122	Rustic Umber

#### TEXTURED METALLIC

251053	Silver
252303	Galaxy
252304	Moonlit Copper
262658	Excalibur
262660	Mystic Brown
353030	Midnight Gold

#### TEXTURED

7220830	Black
7221830	Dark Pewter
7222830	Forest Green
7223830	Sandstone
7224830	Nickel
7225830	White
7226830	Bronze
7227830	Rust
7228830	Sage
241253	Dark Olive
241254	Dark Taupe
241255	Dark Brown
241256	Old Brick

## PRODUCT APPLICATION

Use outdoors or in a well-ventilated area such as an open garage. Use when temperature is between 50°-90°F (10°-32°C) and humidity is below 70% to ensure proper drying. Do not apply to surfaces that, when heated, exceed 200°F (93°C) or galvanized metal. Avoid spraying in very windy, dusty conditions. Cover surrounding area to protect from spray mist.

## SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile.

**WARNING!** If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

## PRIMING

Use of a Stops Rust® Primer provides added corrosion protection, superior adhesion and hiding and is especially recommended for bare wood and metal.

7769	Rusty Metal Primer
7780	Clean Metal Primer



# STOPS RUST® TEXTURED SPRAYS

## PRODUCT APPLICATION (cont.)

### APPLICATION

Shake can vigorously for one minute after mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 18-24" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. It is recommended to apply a light first coat, target 50% coverage. Apply 2 or more light coats a few minutes apart.

### DRY AND RECOAT TIMES

Based on 70°F (21°C) 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 15 minutes, dry to handle in 1-2 hours, and fully dry in 48 hours. Primers may be top coated immediately. Apply a second coat or clear coat within 1 hour or after 48 hours.


## PRODUCT APPLICATION (cont.)

### CLEAN UP

Wipe off tip before storing. Clean up wet paint with Xylene or mineral spirits. Throw away empty can in trash pickup. Do not burn or place in home trash compactor.

### CLOGGING

If valve clogs, twist and pull off spray tip and rinse it in a solvent such as mineral spirits. Do not stick a pin or other objects into the stem.

	<b>TECHNICAL DATA</b>	<b>SRT-09</b>
	<b>STOPS RUST®</b> <b>TEXTURED SPRAYS</b>	

## PHYSICAL PROPERTIES

TEXTURED SPRAYS		
Resin Type		Solvent Acrylic
Pigment Type		Varies with color
MIR		Textured 0.80 Max Multicolor Texture 1.05 Max Textured Metallic 1.25 Max
Fill Weight		12 ounces
Solvents		Acetone, Toluene, Xylene
Recommended Dry Film Thickness (DFT) Per Coat		1.0-2.0 mils (25-50μ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		4-8 sq. ft./can (0.37-0.74 m <sup>2</sup> /can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	15 minutes
	Handle	1-2 hours
	Recoat	Apply a second coat or clear coat within 1 hour or after 48 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation  
11 Hawthorn Parkway  
Vernon Hills, Illinois 60061

Phone: 877-385-8155  
www.rustoleum.com

Form: GDH-729  
Rev.: 121919