



TECHNICAL DATA

ATO-39

CALIPER PAINT

DESCRIPTION AND USES

Rust-Oleum® Caliper Paint is a durable coating that allows you to customize car or truck brake calipers, drums and springs. Caliper Paint is formulated to resist brake dust and high temperatures that can be produced from harsh braking conditions.

PRODUCTS

SKU (8 fl. oz.)	Description
257227	Red Caliper Paint
251592	Black Caliper Paint
251593	Blue Caliper paint
251595	Silver Caliper Paint

PAINTING APPLICATION

PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Apply when temperature is between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying.

SURFACE PREPARATION

Clean the brake calipers with Rust-Oleum Caliper Cleaner (251597) and follow all directions accordingly. Brake dust may contain asbestos. Remove all loose brake dust with a HEPA type vacuum and wear NIOSH approved respiratory protection. Mask off the surrounding area prior to painting. Cover the brake bleeder screws, brake lines and caliper piston boots with the enclosed masking tape. **NOTE: Do not use compressed air to clean calipers as it could increase your risk to air-borne asbestos.**

PRODUCT APPLICATION (cont.)

WARNING: If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log onto www.epa.gov/lead.

APPLICATION

Stir can contents thoroughly before application. Apply paint to the caliper or drum in thin, even strokes using the enclosed brush to cover the entire surface. For the best appearance, apply 2-3 coats waiting 5 minutes between coats. Recoat after 24 hours if needed.

DRY & RECOAT

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 2-4 hours, to handle in 5-9 hours and is fully dry after 24 hours. Wait 5-9 hours before reinstalling wheels and 24 hours before resuming use of the vehicle.

CLEAN-UP

Clean up wet paint with xylene or Rust-Oleum® Mineral Spirits.



TECHNICAL DATA

CALIPER PAINT

PHYSICAL PROPERTIES

		CALIPER PAINT
Resin Type		Modified Alkyd
Pigment Type		Organic
Solvents		Stoddard Solvent Blend
Weight	Per Gallon	7.7 lbs.
	Per Liter	0.92 kg
Solids	By Weight	48.0%
	By Volume	37.5%
VOC		<475 g/l (3.95 lbs./gal.)
Recommended Dry Film Thickness (DFT) per Coat		3.0-4.0 mils (75-100μ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		8-10 sq.ft./half-pint
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	2-4 hours
	Handle	5-9 hours
	Fully Dry	24 hours
Shelf Life		5 years
Flash Point		104°F (40°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.