

• TRUSTED QUALITY SINCE 1921 •

RUST-OLEUM®
SPECIALTY

SPECIALTY DRY ERASE QUART

DESCRIPTION AND USES

Dry Erase Paint is a smooth, hard finish that creates a unique white writeable-erasable surface. Once dry, simply use any dry erase markers to draw or write messages and then erase. Application is easy and it has minimal odor making it safe to use indoors. Dry Erase is ideal for use on interior surfaces such as drywall, Masonite, wood, cement and metal. Not recommended for use in commercial applications. **For Commercial applications, please refer to the Professional Dry Erase products White 261362 or 261363.**

PRODUCTS

FINISHES

241140 Glossy White

PRODUCT APPLICATION

SURFACE PREPARATION

Surfaces must be clean, dry, and free of dirt, grease and oil. Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with detergent or other suitable cleaner. Rinse thoroughly with fresh water and allow to fully dry.

Lightly sand the surface that is to be painted. Remove dust from sanding with a lint-free cloth. **WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the U.S.EPA/Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

MIXING

Briefly stir each can before mixing. Pour Part A into Part B and stir thoroughly until the paint is uniform in color (about 2 minutes). No waiting time is required after mixing. **IMPORTANT!** Apply activated Dry Erase Paint within 2 hours of mixing.

PRODUCT APPLICATION (cont.)

APPLICATION

Apply only when air and surface temperatures are between 50-90°F (10-32°C) and the relative humidity is below 85% to ensure proper drying. If applying dry erase on a new piece of drywall, Masonite, cement, or wood, use a white latex primer first, following the manufacturer's directions. A primer is not needed for existing drywall that is already painted or on metal surfaces. With painter's tape, tape around the area you wish to paint before beginning. Pour paint into a paint tray. Use a dense foam roller that is designed to give a smooth finish. For smaller surfaces, use a foam brush.

Dry and recoat times are based on 77°F (25°C) and 50% relative humidity. Allow more time at cooler temperatures. Recoat after 20-30 minutes. For best results, apply over a white or light colored surface with a minimum of 2 coats. When applying over darker surfaces, 3 coats are recommended. The surface dries to the touch in 1 hour. After 1 hour, remove painter's tape that was used to mask the area. Then allow the Dry Erase surface to cure for 2 days before applying any markings. Once fully cured, Dry Erase markers may be applied to the surface and then wiped off with an eraser or lint-free cloth. If after erasing, a hint a marking remains, simply use a dry erase cleaner or any other general household cleaner to remove marks. Do not use abrasive cleaners, pads, or cloths. Let surface dry before using dry erase markers again.

CLEAN-UP

Clean brush and other application tools immediately with soap and water.

TECHNICAL DATA

SPECIALTY DRY ERASE QUART

PHYSICAL PROPERTIES

		DRY ERASE (WHITE, ACTIVATED)
Resin Type		Epoxy
Pigment Type		Titanium Dioxide
Solvents		Water, Glycol
Weight	Per Gallon	9.4 lbs
	Per Liter	1.12 kg/l
Solids	By Weight	47.8%
	By Volume	41.2%
Volatile Organic Compounds		<100 g/l (0.83 lbs./gal.)
Recommended Dry Film Thickness (DFT) per Coat		1.5 - 2.0 mils
Wet Film to Achieve DFT (unthinned material)		3.5 - 5.0 mils
Theoretical Coverage at 1 mil DFT (25µ)		165 sq.ft. /quart
Practical Coverage at Recommended DFT (assumes 15% material loss)		(2 coats) 35-45 sq.ft./quart
Mixing Ratio		19 oz. Part B to 8 oz. Part A
Dry Times at 70°F (21°C) and 50% Relative Humidity	Tack-free	1 hour
	Handle	2 hours
	Recoat	2 hours
Dry Heat Resistance		n/a
Shelf Life		1 year
Safety Information	Flash Point	>102°F
	Contains	—
	Warning!	For additional information, see MSDS.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.